



## Material - IS 3168 CuZn37

## Standard Specification for Brass Strip and Foil for Deep Drawing

**Group - Non-Ferrous Copper Alloy** 

Sub Group - IS 3168 Brass Strip and Foil for Deep Drawing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Strip and Foil** 

Chemical Composition			Heat Treatment	
Lead	Pb %	0.100 max.		
Iron	Fe %	0.050 max.		
Other	Ot%	0.250 max.		
Copper	Cu %	61.500 - 64.500	Cold Rolled or Annealing & Tempering	ing & Tempering
Zinc	Zn %	Balance		
-	-			
-	-	-		
-	-	-		_
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	-
-	-		Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	ntry Grade Belong to the Industry	
CuZn30	IS	India	Strip and Foil	
CZ 106	BS	British	Sheet, Strip and Foil	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.