



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - IS 3331 Grade I

**Standard Specification for Copper and Brass Strips/Foils for Radiator Cores**

**Group - Non-Ferrous Copper Alloy**

**Sub Group - IS 3331 Copper and Brass Strips/Foils for Radiator Cores**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Strip and Foil**

Chemical Composition			Heat Treatment	
Lead	Pb %	0.020 max.	Cold Rolled or Annealing or Half Hardening or Hardening or Tempering	
Iron	Fe %	0.050 max.		
Tin	Sn %	0.030 max.		
Other	Ot%	0.200 max.		
Copper	Cu %	68.500 - 71.500		
Zinc	Zn %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in HV 85 max. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +91846916029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

**ONE STOP SOLUTION FOR METAL PARTS**