

Material - IS 3444 Grade 22A

Standard Specification for Castings, Iron-Chromium, Iron-Choromium-Nickel Corrosion Resistant, for General Application

Group - Non-Ferrous Nickel Alloys

Sub Group - IS 3444 Grade 22A Castings, Iron-Chromium, Iron-Choromium-Nickel Corrosion Resistant, for General Application

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 max.		
Silicon	Si %	1.250 max.		
Manganese	Mn %	1.500 max.	As-Cast or Annealing or Age Hardning	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.030 max.		
Copper	Cu %	26.000 - 33.000		
Iron	Fe %	3.500 max.		
Nickel	Ni %	Balance		_
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	23 min.
-	-	-	Reduction of Area in %	
-	-	-	Hardness in BHN	-
-	-		Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
A 743 Grade M-35-1	ASTM	USA	Casting		
A 744 Grade M-35-1	ASTM	USA	Casting		
-	-		-		
-	-	-	-		
-	-	-	-		
-	-	-	-		
-	-	-	-		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.