

Material - IS 4171

Standard Specification for Copper Wires for General Engineering Purposes

Group - Non-Ferrous Copper Alloy

Sub Group - IS 4171 Copper Wires for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Wire

Chemical Composition			Heat Treatment	
Tin	Sn %	0.010 max.	As Raw	
Lead	Pb %	0.010 max.		
Iron	Fe %	0.030 max.		
Nickel	Ni %	0.100 max.		
Arsenic	As %	0.05 max.		
Antimony	Sb %	0.005 max.		
Bismuth	Bi %	0.003 max.		
Phosphorus	Р%	0.0150 - 0.060		
Selenium + Tellurium	Se % + Te%	0.020 max.	Mechanical Properties	
Other	Ot%	0.060 max.	Tensile Strength in Mpa	230 max.
Copper	Cu %	99.500 max.	Yield Strength in Mpa	-
-	-	-	Elongation in %	13 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS