



Material - IS 617 4520

Standard Specification for Aluminium Alloy Castings

Group - Non-Ferrous Alumium Alloy

Sub Group - IS 617 Aluminium and Aluminium Alloy Ingots and Castings for General Engineering Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.700 - 2.500		
Iron	Fe %	1.000 max.		
Magnesium	Mg %	0.300 max.		
Manganese	Mn %	0.500 max.	As-Cast	
Nickel	Ni %	0.500 max.		
Lead	Pb %	0.300 max.		
Silicon	Si %	9.000 - 11.000		
Tin	Sn %	0.200 max.		
Zinc	Zn %	2.000 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	-
-	-		Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-		Hardn <mark>ess in BH</mark> N	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
AA307	AS	Australia	Ingot and Casting	
307	AS	Australia	Ingot and Casting	
LM2	BS	British	Ingot and Casting	
ADC12	JIS	Japan	Ingot and Casting	
ADC12Z	JIS	Japan	Ingot and Casting	
383	AA	USA	Ingot and Casting	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.