GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 736 24345

Standard Specification for Wrought Aluminium and Aluminium Alloy Plate for General Engineering Purposes

Group - Non-Ferrous Aluminium Alloy

Sub Group - IS 736 24345 Wrought Aluminium and Aluminium Alloy Plate for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Plate

Chemical Composition		
Copper	Cu %	3.800 - 5.000
Magnesium	Mg %	0.200 - 0.800
Silicon	Si %	0.500 - 1.200
Iron	Fe %	0.700 max.
Manganese	Mn %	0.300 - 1.200
Zinc	Zn %	0.200 max.
Titanium	Ti %	0.300 max.
Chromium	Cr %	0.300 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Solution Annealing & Naturally Aging or Solution Annealing & Precipitation Treated

Mechanical Properties	
Tensile Strength in Mpa	150 min.
Yield Strength in Mpa	-
Elongation in %	10 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
IS 737 24345	IS	India	Steel and Strip
SB-209 2014	ASME	USA	Sheet and Plate
SB-210 2014	ASME	USA	Tubing
IS 733 24345	IS	India	Bars and Rods
B 211 2014	ASTM	USA	Bars, Rods and Wire
B 210 2014	ASTM	USA	Tubing
B 209 2014	ASTM	USA	Sheet and Plate

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.