GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 736 51000-A

Standard Specification for Wrought Aluminium and Aluminium Alloy Plate for General Engineering Purposes

Group - Non-Ferrous Aluminium Alloy

Sub Group - IS 736 51000-A Wrought Aluminium and Aluminium Alloy Plate for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Plate

Chemical Composition		
Copper	Cu %	0.200 max.
Magnesium	Mg %	0.500 - 1.100
Silicon	Si %	0.600 max.
Iron	Fe %	0.700 max.
Manganese	Mn %	0.200 max.
Zinc	Zn %	0.250 max.
Chromium	Cr %	0.100 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Strain Hardening & Partially Annealing

Mechanical Properties	
Tensile Strength in Mpa	105 min.
Yield Strength in Mpa	-
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
IS 737 51000-A	IS	India	Steel and Strip
IS 21 51000-A	IS	India	Sheet and Strip
209-1 Al Mg1(B)	ISO	International	Extrusion, Rods & Bars
209-1 5005	ISO	International	Extrusion, Rods & Bars
209-1 3105	ISO	International	Extrusion, Rods & Bars
Al Mn0,5Mg0,5	ISO	International	Extrusion, Rods & Bars
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.