GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 736 53000

Standard Specification for Wrought Aluminium and Aluminium Alloy Plate for General Engineering Purposes

Group - Non-Ferrous Aluminium Alloy

Sub Group - IS 736 53000 Wrought Aluminium and Aluminium Alloy Plate for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Plate

Chemical Composition		
Copper	Cu %	0.100 max.
Magnesium	Mg %	2.800 - 4.000
Silicon	Si %	0.600 max.
Iron	Fe %	0.700 max.
Manganese	Mn %	0.500 max.
Zinc	Zn %	0.200 max.
Titanium	Ti %	0.200 max.
Chromium	Cr %	0.250 max.
Cr + Mn	Cr% + Mn%	0.500 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Strain Hardening & Partially Annealing

Mechanical Properties	
Tensile Strength in Mpa	215 min.
Yield Strength in Mpa	-
Elongation in %	12 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
IS 737 53000	IS	India	Steel and Strip
IS 733 53000	IS	India	Bars and Rods
IS 1285 53000	IS	India	Tubing
3522 Al-Mg3	ISO	International	Casting
1725 3.3541.01	DIN	Germany	Casting
1725 3.3541.02	DIN	Germany	Casting
1725 3.3541.09	DIN	Germany	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.