



Material - IS 7811

Standard Specification for Phosphor Bronze Rods and Bars

Group - Non-Ferrous Copper Alloy

Sub Group - IS 7811 Phosphor Bronze Rods and Bars

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod and Bar

Chemical Composition			Heat Treatment	
Tin	Sn %	4.200 - 5.500	As Raw	
Phosphorus	P %	0.020 - 0.400		
Lead	Pb %	0.020 max.		
Zinc	Zn %	0.300 max.		
Other	Ot%	0.500 max.		
Copper	Cu %	Balance		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	500 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
-	-	-	-	
-	-	ı	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.