



## Material - IS 8362 90/10 Copper - Nickel - Iron

**Standard Specification for Copper and Copper Alloy Rolled Plates for Condensers and Heat Exchangers**

**Group - Non-Ferrous Copper Alloy**

**Sub Group - IS 8362 Copper and Copper Alloy Rolled Plates for Condensers and Heat Exchangers**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Plate**

Chemical Composition			Heat Treatment	
Zinc	Zn %	1.000 max.	As Raw	
Nickel	Ni %	9.000 - 11.000		
Iron	Fe %	1.000 - 2.000		
Manganese	Mn %	0.300 - 0.800		
Sulphur	S %	0.030 max.		
Lead	Pb %	0.050 max.		
Other	Ot%	0.300 max.		
Copper	Cu %	86.500 min.		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	275 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.