



Material - IS 8362 Copper - Silicon

Standard Specification for Copper and Copper Alloy Rolled Plates for Condensers and Heat Exchangers

Group - Non-Ferrous Copper Alloy

Sub Group - IS 8362 Copper and Copper Alloy Rolled Plates for Condensers and Heat Exchangers

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate

Chemical Composition			Heat Treatment	
Zinc	Zn %	1.500 max.	As Raw	
Iron	Fe %	0.800 max.		
Manganese	Mn %	0.500 - 1.500		
Lead	Pb %	0.050 max.		
Silicon	Si %	2.800 - 3.800		
Other	Ot%	0.500 max.		
Copper	Cu %	94.800 min.		
-	-	-	Mechanical Properties Tensile Strength in Mpa 340 min. Yield Strength in Mpa - Elongation in % 31 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.