

## Material - IS 8362 CuZn37 (A)

Standard Specification for Copper and copper Alloy Rolled Plates for Condensers and Heat Exchangers

## **Group - Non-Ferrous Copper Alloy**

Sub Group - IS 8362 Copper and copper Alloy Rolled Plates for Condensers and Heat Exchangers Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Plates

Chemical Composition			Heat Treatment	
Tin	Sn %	1.000 - 1.500		
Other	Ot%	0.750 max.		
Copper	Cu %	61.000 - 64.000	I	
Zinc	Zn %	Balance	Normalizing or Annealing or Tempering	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	310 - 360
	-	-	Yield Strength in Mpa	-
	-	-	Elongation in %	18 min.
	-	-	Reduction of Area in %	-
-	-	-	Hardne <mark>ss in BHN</mark>	-
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CuZn36Sn1	IS	India	Plate	
464B	AS	Australia	Forging	
CZ 112	BS	British	Rod and Section	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## **ONE STOP SOLUTION FOR METAL PARTS**