



## Material - IS 9088 Alloy 1

### Standard Specification for Universal Head Nickel Alloy Rivets for Aircraft

Group - Non-Ferrous Nickel Alloys

Sub Group - IS 9088 Alloy 1 Universal Head Nickel Alloy Rivets for Aircraft

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.160 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.300 - 2.000		
Aluminium	Al %	0.500 max.		
Sulphur	S %	0.024 max.		
Iron	Fe %	2.500 max.		
Copper	Cu %	28.000 - 34.000		
Nickel	Ni %	Balance		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	490 min.
-	-	-	Yield Strength in Mpa	350 min.
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.