



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - IS 9713 ETP

Standard Specification for Hot Rolled Electrolytic Copper Wire Rod for Electrical Conductor

Group - Non-Ferrous Copper Alloy

Sub Group - IS 9713 Hot Rolled Electrolytic Copper Wire Rod for Electrical Conductor

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Wire and Rod

Chemical Composition			Heat Treatment	
Lead	Pb %	0.005 max.	As Raw	
Oxygen	O %	0.045 max.		
Copper + Silver	Cu% + Ag%	99.90 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	200 min.
			Yield Strength in Mpa	-
			Elongation in %	46 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS