



Material - ISO 121 Mg-Al8Zn

Standard Specification for Magnesium-Aluminium-Zinc Alloy Casting

Group - Non-Ferrous Magnesium-Aluminium-Zinc Alloy

Sub Group - ISO 121 Magnesium-Aluminium-Zinc Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Wire

Chemical Composition			Heat Treatment	
Zinc	Zn %	0.200 - 1.000	As-Cast or Solution Treated or Fully Treated	
Manganese	Mn %	0.150 - 0.600		
Silicon	Si %	0.300 max.		
Iron	Fe %	0.050 max.		
Copper	Cu %	0.200 max.		
Nickel	Ni %	0.010 max.		
Aluminium	Al %	7.500 - 9.000		
Magnesium	Mg %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	140 min.
-	-	-	Yield Strength in Mpa	75 min.
-	-	-	Elongation in %	1 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
MBD-AZ80	JIS	Japan	Bar and Wire
MS-AZ80	JIS	Japan	Shape
MWD-AZ80	JIS	Japan	Bar and Wire
B107 AZ80A	ASTM	USA	Bar, Rod, Tube and Wire
B951 AZ80A	ASTM	USA	Bar and Wire
MB3	KS	Korea	Bar
MgAl8Zn	DIN	Germany	Bar and Wire

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.