



## Material - ISO 1338 CuSn12Ni2

Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ISO 4382 Cast Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Ingot and Casting** 

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.150 max.		
Manganese	Mn %	0.200 max.		
Nickel	Ni %	1.500 - 2.000		
Phosphorus	P %	0.050 max.		
Lead	Pb %	0.200 max.		
Sulphur	S %	0.050 max.		
Antimony	Sb %	0.100 max.		•
Silicon	Si %	0.010 max.	Mechanical Properties	
Tin	Sn %	11.200 - 13.000	Tensile Strength in Mpa	280 - 300
Zinc	Zn %	0.400 max.	Yield Strength in Mpa	160 - 180
Copper	Cu %	84.500 - 87.300	Elongation in %	8 - 12
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CT2	BS	British	Ingot and Casting	
C91700	AS	Australia	Ingot and Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.