



Material - ISO 301 ZL3

Specification Standards for Zinc alloy ingots intended for castings

Group - Non-Ferrous Zinc Alloy

Sub Group - ISO 301 Zinc alloy ingots intended for castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.900 - 4.300	As-Cast or Aging	
Cadmium	Cd %	0.003 max.		
Copper	Cu %	0.100 max.		
Iron	Fe %	0.035 max.		
Magnesium	Mg %	0.030 - 0.060		
Lead	Pb %	0.004 max.		
Tin	Sn %	0.0015 max.		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	285 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	82 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Zamak 2	ANSI/AA	USA	Casting
ZDC 2	JIS	Japan	Casting
ZDC 2	KS	Korea	Casting
B240 AG40A	ASTM	USA	Casting
B240 Zamak 3	ASTM	USA	Casting
GD-ZnAl4	DIN	Germany	Casting
903	SAE	USA	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.