



## Material - ISO 3522 Al 99.7

### Standard Specification for Aluminium and Aluminium Alloys

Group - Non-Ferrous Aluminium Alloy

Sub Group - ISO 3522 for Aluminium and Aluminium Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	0.100 max.	As-Cast	
Iron	Fe %	0.200 max.		
Copper	Cu %	0.010 max.		
Manganese	Mn %	0.050 max.		
Magnesium	Mg %	0.020 max.		
Chromium	Cr %	0.004 max.		
Zinc	Zn %	0.040 max.		
Aluminium	Al %	99.700 min		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	0
			Yield Strength in Mpa	0
			Elongation in %	0
			Reduction of Area in %	-
			Hardness in HBW	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN Al 1070	DIN	Germany	Wire and Rod
EN Al 1070	SFS	Finland	Wire and Rod
EN Al 1070	ONORM	Australia	Wire and Rod
EN Al 1070	BS	British	Wire and Rod
EN Al 1070	UNI	Italy	Wire and Rod
EN Al 1070	UNS	USA	Wire and Rod
EN Al 1070	MSZ	Hungary	Wire and Rod

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.