



## Material - ISO 3522 Al Si11Cu3(Fe)

Standard Specification for Aluminium and Aluminium Alloys

**Group - Non-Ferrous Aluminium Alloy** 

Sub Group - ISO 3522 for Aluminium and Aluminium Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Casting** 

Chemical Composition			Heat Treatment	
Silicon	Si %	9.600 - 12.000		
Iron	Fe %	1.300 max.		
Copper	Cu %	1.500 - 3.500	As-Cast	
Manganese	Mn %	0.600 max.		
Magnesium	Mg %	0.350 max.		
Nickel	Ni %	0.450 max.		
Zinc	Zn %	1.700 max.		
Lead	Pb %	0.250 max.		
Tin	Sn %	0.250 max.	Mechanical Properties	
Titanium	Ti %	0.250 max.	Tensile Strength in Mpa	240 min.
Aluminium	Al %	Balance	Yield Strength in Mpa	140 min.
0	0	0	Elongation in %	-
0	0	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	80 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
AA307	AS	Australia	Ingot and Casting	
307	AS	Australia	Ingot and Casting	
4520	IS	India	Ingot and Casting	
ADC12	JIS	Japan	Ingot and Casting	
ADC12Z	JIS	Japan	Ingot and Casting	
383.0	AA	USA	Ingot and Casting	
Al Si11Cu3(Fe)	JIS	Japan	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.