



Material - ISO 3522 Al Si9Cu3(Fe)

Standard Specification for Aluminium and Aluminium Alloys

Group - Non-Ferrous Aluminium Alloy

Sub Group - ISO 3522 for Aluminium and Aluminium Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	8.000 - 11.000		
Iron	Fe %	1.300 max.		
Copper	Cu %	2.000 - 4.000		
Manganese	Mn %	0.200 - 0.550	As-Cast	
Magnesium	Mg %	0.050 - 0.550		
Chromium	Cr %	0.150 max.		
Nickel	Ni %	0.500 max.		
Zinc	Zn %	1.200 max.		
Lead	Pb %	0.350 max.	Mechanical Properties	
Tin	Sn %	0.250 max.	Tensile Strength in Mpa	240 min.
Titanium	Ti %	0.250 max.	Yield Strength in Mpa	140 min.
Other	Ot%	0.250 max.	Elongation in %	-
Aluminium	Al %	Balance	Reduction of Area in %	-
-	-	-	Hardness in HBW	80 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
EN AC-46000	DIN	Germany	Casting	
EN AC-46000	BS	British	Casting	
EN AC-46000	ASME	USA	Casting	
EN AC-46000	UNI	Italy	Casting	
EN AC-46000	AFNOR NF	France	Casting	
EN AC-46000	UNE	Spain	Casting	
EN AC-46000	SFS	Finland	Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.