



Material - ISO 4382 CuAl10Fe5Ni5

Standard Specification for Cast Copper Alloys for Solid and Multilayer Thick-Walled Plain Bearings

Group - Non-Ferrous Copper Alloy

Sub Group - ISO 4382 Cast Copper Alloys for Solid and Multilayer Thick-Walled Plain Bearings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.000 - 11.000	As-Cast	
Iron	Fe %	3.500 - 5.500		
Manganese	Mn %	3.000 max.		
Nickel	Ni %	3.500 - 6.500		
Lead	Pb %	0.100 max.		
Silicon	Si %	0.100 max.		
Tin	Sn %	0.200 max.		
Zinc	Zn %	0.500 max.		
Copper	Cu %	Balance		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	600 - 740
-	-	-	Yield Strength in Mpa	250 - 340
-	-	-	Elongation in %	10 - 12
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	140 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AB2	BS	British	Ingot and Casting
958C	AS	Australia	Ingot and Casting
C95810	AS	Australia	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.