



Material - ISO 4382 CuPb10Sn10

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloy Sub Group - ISO 4382 Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.		
Iron	Fe %	0.250 max.		
Manganese	Mn %	0.200 max.	As-Cast	
Nickel	Ni %	2.000 max.		
Phosphorus	Р%	0.100 max.		
Lead	Pb %	8.000 - 11.000		
Sulphur	S %	0.100 max.		
Antimony	Sb %	0.500 max.		_
Silicon	Si %	0.010 max.	Mechanical Properties	
Tin	Sn %	9.000 - 11.000	Tensile Strength in Mpa	180 - 220
Zinc	Zn %	2.000 max.	Yield Strength in Mpa	80 - 140
Copper	Cu %	Balance	Elongation in %	3 - 7
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	65 - 70
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
LB2	BS	British	Casting	
937B	AS	Australia	Ingot and Casting	
C93700	AS	Australia	Ingot and Casting	
-	-		-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.