



Material - ISO CuZn39Pb3

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group - Non Ferrous Copper Alloys

Sub Group - ISO CuZn39Pb3 Copper and Copper Alloy Rod for Free Machining Purpose

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.350 max.	As Raw or Solution Heat Treated	
Lead	Pb %	2.500 - 3.500		
Copper	Cu %	56.000 - 59.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	370 min.
			Yield Strength in Mpa	210 min.
			Elongation in %	11 min.
			Reduction of Area in %	-
			Hardness in BHN	110 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn39Pb3	DIN	Germany	Rod
CuZn39Pb3	GOST	Russia	Rod
LS58-3	GOST	Russia	Rod
CU 3	ISO	International	Rod
C 3604 BD	JIS	Japan	Rod
C 3604 BE	JIS	Japan	Rod
C 3604 BF	JIS	Japan	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.