



Material - JIS C 2800 W

Standard Specification for Copper and Copper Alloy Rod for Free Machining Purpose

Group - Non Ferrous Copper Alloys

Sub Group - JIS C 2800 W Copper and Copper Alloy Rod for Free Machining Purpose

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.020 max.	As Raw or Solution Heat Treated	
Iron	Fe %	0.020 max.		
Manganese	Mn %	0.020 max.		
Nickel	Ni %	0.020 max.		
Lead	Pb %	0.020 max.		
Copper	Cu %	59.000 - 63.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	315 - 705
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	5 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 12164 CuZn39Pb0.5	DIN	Germany	Rod
5163	SS	Sweden	Rod
C 3710 R	JIS	Japan	Rod
C 3712 BD	JIS	Japan	Rod
C 3712 BE	JIS	Japan	Rod
C 3712 BF	JIS	Japan	Rod
C 4640 P	JIS	Japan	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.