

## Material - JIS H 5203 MgAl8Zn1 Class 2A

Standard Specification for Magnesium Alloy Casting

Group - Non-Ferrous Magnesium Alloy

Sub Group - JIS H 5203 Magnesium Alloy Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	7.000 - 9.500		
Copper	Cu %	0.350 max.	As-Cast or Solution Treated	
Iron	Fe %	0.050 max.		
Manganese	Mn %	0.150 max.		n Treated
Nickel	Ni %	0.020 max.		
Silicon	Si %	0.500 max.		
Zinc	Zn %	0.300 - 2.000		
Magnesium	Mg %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	140 min.
-	-	-	Yield Strength in Mpa	75 min.
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
MgAl8Zn1	ISO	International	Bar and Wire	
MAG 7	BS	British	Ingot and Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS