



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - JIS H 5302 ADC12Z

Standard Specification for Aluminium Alloy Castings

Group - Non-Ferrous Aluminium Alloy

Sub Group - JIS H 5302 Aluminium Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	1.500 - 3.500	As-Cast	
Iron	Fe %	1.300 max.		
Magnesium	Mg %	0.300 max.		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.500 max.		
Lead	Pb %	0.200 max.		
Silicon	Si %	9.600 - 12.000		
Tin	Sn %	0.200 max.		
Zinc	Zn %	3.000 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa - Yield Strength in Mpa - Elongation in % - Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AA307	AS	Australia	Ingot and Casting
307	AS	Australia	Ingot and Casting
4520	IS	India	Ingot and Casting
ADC12	JIS	Japan	Ingot and Casting
LM2	BS	British	Ingot and Casting
383	AA	USA	Ingot and Casting
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS