



## Material - JIS NNCP

### Standard Specification for Nickel and nickel Alloy Sheet and Plate

Group - Non-Ferrous Nickel Alloys

Sub Group - JIS NNCP Nickel and nickel Alloy Sheet and Plate

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Sheet and Plate

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.350 max.		
Manganese	Mn %	0.350 max.		
Copper	Cu %	0.250 max.		
Sulphur	S %	0.010 max.		
Iron	Fe %	0.400 max.		
Nickel	Ni %	99.000 min.		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	380 min.
-	-	-	Yield Strength in Mpa	100 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 160 N02200	ASTM	USA	Rod and Bar
B 161 N02200	ASTM	USA	Pipe and Tube
B 162 N02200	ASTM	USA	Plate, Sheet and Strip
B 163 N02200	ASTM	USA	Tube
B 564 N02200	ASTM	USA	Forging
B 725 N02200	ASTM	USA	Pipe
N02200	UNS	USA	Pipe

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.