



Material - JIS H 5203 MC3

Standard Specification for Magnesium Alloy Castings

Group - Non-Ferrous Magnesium Alloy

Sub Group - JIS H 5203 Magnesium Alloy Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.000 - 10.000	As-Cast or Solution Treated or Fully Treated	
Copper	Cu %	0.200 max.		
Iron	Fe %	0.050 max.		
Manganese	Mn %	0.100 - 0.500		
Nickel	Ni %	0.010 max.		
Other	Ot%	0.300 max.		
Silicon	Si %	0.300 max.		
Zinc	Zn %	1.500 - 2.500		
Magnesium	Mg %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	140 - 235
-	-	-	Yield Strength in Mpa	75 - 110
-	-	-	Elongation in %	1 - 6
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Mg-Al9Zn2	ISO	International	Bar and Wire
B80 AZ92A	ASTM	USA	Casting
B93 AZ92A	ASTM	USA	Casting
B199 AZ92A	ASTM	USA	Casting
B275 AZ92A	ASTM	USA	Casting
B403 AZ92A	ASTM	USA	Casting
B951 AZ92A	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.