



Material - KS D2320 CACIn406

Standard Specification for Copper Alloys Ingot for Casting

Group - Non-Ferrous Copper Alloy

Sub Group - KS D2320 Copper Alloys Ingot for Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.300 max.		
Nickel	Ni %	0.800 max.		
Phosphorus	P %	0.030 max.		
Lead	Pb %	4.000 - 6.000		
Antimony	Sb %	0.200 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	4.000 - 6.000		
Zinc	Zn %	4.000 - 6.000		
Copper	Cu %	83.000 - 87.000		
-	-	-	Mechanical Properties Tensile Strength in Mpa 250 min. Yield Strength in Mpa 110 min. Elongation in % 13 min. Reduction of Area in % - Hardness in HB 65 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C93600	UNS	USA	Rod, Bar, Tube and Shapes
B30 C93600	ASTM	USA	Ingot and Casting
B66 C93600	ASTM	USA	Casting
B271 C93600	ASTM	USA	Casting
B505 C93600	ASTM	USA	Casting
SB-271 C93600	ASME	USA	Casting
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.