



Material - KS NW6601

Standard Specification for Nickel and Nickel Alloy Wire and Drawing Stock

Group - Non-Ferrous Nickel Alloys

Sub Group - KS NW6601 Nickel and Nickel Alloy Wire and Drawing Stock

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 max.	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	21.000 - 25.000		
Aluminium	Al %	1.000 - 1.700		
Copper	Cu %	1.000 max.		
Sulphur	S %	0.015 max.		
Nickel	Ni %	58.000 - 63.000		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	515 min.
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Inconel 601	SAE	USA	Plate, Sheet and Strip
N06601	UNS	USA	Plate, Sheet and Strip
NiCr23Fe15Al	JIS	Japan	Plate, Sheet and Strip
NW6601	JIS	Japan	Plate, Sheet and Strip
NiCr23Fe15Al	KS	Korea	Wire
B516 N06601	ASTM	USA	Tube
F2281 601	ASTM	USA	Bolts, Hex Cap Screws and Studs

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.