



## Material - MSZ EN 1982 CC490K

### Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - MSZ EN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.010 max.	As-Cast	
Iron	Fe %	0.500 max.		
Nickel	Ni %	2.000 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	3.000 - 6.000		
Sulphur	S %	0.100 max.		
Antimony	Sb %	0.300 max.		
Silicon	Si %	0.010 max.		
Tin	Sn %	2.000 - 3.500	Mechanical Properties	
Zinc	Zn %	7.000 - 9.500	Tensile Strength in Mpa	180 - 220
Cu + Ni	Cu%+Ni%	81.000 - 86.000	Yield Strength in Mpa	85 - 100
-	-	-	Elongation in %	12 - 15
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	60 - 70
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB490K	BS	British	Ingot and Casting
CC490K	UNI	Italy	Ingot and Casting
CuSn3Zn8Pb5-C	UNI	Italy	Ingot and Casting
CuSn3Zn8Pb5-C	MSZ	Hungary	Ingot and Casting
CC490K	AFNOR NF	France	Ingot and Casting
CuSn3Zn8Pb5-C	AFNOR NF	France	Ingot and Casting
CC490K	SFS	Finland	Ingot and Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.