



## Material - MSZ EN 1982 CuZn25Al5Mn4Fe3-C

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - MSZ EN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.000 - 7.000	As-Cast	
Iron	Fe %	1.500 - 4.000		
Manganese	Mn %	2.500 - 5.000		
Nickel	Ni %	3.000 max.		
Phosphorus	P %	0.030 max.		
Lead	Pb %	0.200 max.		
Antimony	Sb %	0.030 max.		
Silicon	Si %	0.100 max.		
Tin	Sn %	0.200 max.	Mechanical Properties	
Cu + Ni	Cu%+Ni%	60.000 - 67.000	Tensile Strength in Mpa	680 - 750
Zinc	Zn %	Balance	Yield Strength in Mpa	450 - 580
-	-	-	Elongation in %	1 - 8
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	180 - 190
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CB762S	BS	British	Ingot and Casting
CC762S	ONORM	Australia	Ingot and Casting
CC762S	BDS	Bulgaria	Ingot and Casting
CC762S	UNI	Italy	Ingot and Casting
CC762S	DIN	Germany	Ingot and Casting
CuZn25Al5Mn4Fe3-C	UNE	Spain	Ingot and Casting
CuZn25Al5Mn4Fe3-C	AFNOR NF	France	Ingot and Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.