



Material - ONORM CW455K

Standard Specification for Copper-Tin Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - ONORM CW455K Copper-Tin Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	As Raw or Solution Heat Treated	
Nickel	Ni %	0.200 max.		
Phosphorus	P %	0.200 - 0.400		
Lead	Pb %	1.500 - 2.500		
Tin	Sn %	3.500 - 4.500		
Zinc	Zn %	0.300 max.		
Other	Ot %	0.200 max.		
Copper	Cu %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	430 min.
-	-	-	Yield Strength in Mpa	220 min.
-	-	-	Elongation in %	8 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HV	125 - 155
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuSn4Pb2P	DIN	Germany	Rod
CuSn4Pb2P	EN	European Union	Rod
CW455K	EN	European Union	Rod
CuSn4Pb2P	ONORM	Australia	Rod
CuSn4Pb2P	MSZ	Hungary	Rod
CW455K	MSZ	Hungary	Rod
CW455K	AFNOR NF	France	Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.