



## Material - ONORM CW714R

### Standard Specification for Copper and Copper Zinc Alloy Rod

Group - Non Ferrous Copper Alloys

Sub Group - ONORM CW714R Copper and Copper Zinc Alloy Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Rod

Chemical Composition			Heat Treatment	
Iron	Fe %	0.100 max.	As Raw or Solution Heat Treated	
Nickel	Ni %	0.300 max.		
Lead	Pb %	0.400 - 1.000		
Tin	Sn %	0.500 - 1.000		
Other	Ot %	0.200 max.		
Copper	Cu %	59.000 - 61.000		
Zinc	Zn %	Balance		
-	-	-	<b>Mechanical Properties</b> Tensile Strength in Mpa      350 - 450 Yield Strength in Mpa      160 - 400 Elongation in %      5 min. Reduction of Area in %      - Hardness in HV      85 - 185 Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuZn37Pb1Sn1	DIN	Germany	Rod
C 4622 BF	JIS	Japan	Rod and Bar
CuZn37Pb1Sn1	ONORM	Australia	Rod
CuZn37Pb1Sn1	NBN	Belgium	Rod
CW714R	NBN	Belgium	Rod
CuZn37Pb1Sn1	EN	European Union	Rod
CW714R	EN	European Union	Rod

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.