



Material - ONORM EN 1982 CB754S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - ONORM EN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Ingot and Casting

Chemical Composition			Heat Treatment			
Aluminium	Al %	0.100 - 0.800	As-Cast			
Iron	Fe %	0.700 max.				
Manganese	Mn %	0.500 max.				
Nickel	Ni %	1.000 max.				
Phosphorus	P %	0.020 max.				
Lead	Pb %	0.500 - 2.400				
Silicon	Si %	0.050 max.				
Tin	Sn %	1.000 max.				
Cu + Ni	Cu%+Ni%	58.000 - 62.000				
Zinc	Zn %	Balance	<th colspan="2">Mechanical Properties</th>		Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-		
-	-	-	Yield Strength in Mpa	-		
-	-	-	Elongation in %	-		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in BHN	-		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC754S	BS	British	Ingot and Casting
CB754S	AFNOR NF	France	Ingot and Casting
CB754S	UNI	Italy	Ingot and Casting
CB754S	BS	British	Ingot and Casting
CuZn39Pb1Al-B	UNE	Spain	Ingot and Casting
CuZn39Pb1Al-B	CSN	Czech Republic	Ingot and Casting
CuZn39Pb1Al-B	MSZ	Hungary	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.