



## Material - ONORM EN 1982 CC752S

Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group - Non-Ferrous Copper Alloy** 

Sub Group - ONORM 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Ingot and Casting** 

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.300 - 0.700	As-Cast	
Arsenic	As %	0.040 - 0.140		
Iron	Fe %	0.300 max.		
Manganese	Mn %	0.100 max.		
Nickel	Ni %	0.200 max.		
Lead	Pb %	1.500 - 2.200		
Antimony	Sb %	0.140 max.		
Sb + As	Sb% + As%	0.140 max.		
Silicon	Si %	0.020 max.	Mechanical Properties	
Tin	Sn %	0.300 max.	Tensile Strength in Mpa	280 - 330
Copper	Cu %	61.500 - 64.500	Yield Strength in Mpa	120 - 250
Zinc	Zn %	Balance	Elongation in %	1.5 - 10
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	70 - 110
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
CB752S	BS	British	Ingot and Casting	
CC752S	UNI	Italy	Ingot and Casting	
CC752S	UNE	Spain	Ingot and Casting	
CC752S	CSN	Czech Republic	Ingot and Casting	
CC752S	BDS	Bulgaria	Ingot and Casting	
CC752S	PN	Poland	Ingot and Casting	
CC752S	MSZ	Hungary	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.