



Material - SAE 5819

Standard Specification for Cobalt-Based alloy, Wire

Group - Non-Ferrous Cobalt Alloys

Sub Group - SAE 5819 Cobalt-Based alloy, Wire

Application - Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry - Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.300		
Silicon	Si %	1.000 max.		
Chromium	Cr %	25.000 - 29.000		
Nickel	Ni %	2.000 - 3.750	As-Cast or Annealing	
Molybdenum	Mo %	5.000 - 6.000		
Iron	Fe %	3.000 max.		
Boron	В %	0.006 max.		
Phosphorus	P %	0.020 max.		_
Manganese	Mn %	1.000 max.	Mechanical Properties	
Sulphur	S %	0.020 max.	Tensile Strength in Mpa	-
Cobalt	Co %	Balance	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HRC	34 min.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Stellite 21	Gravity	India	Casting	
5385	SAE	USA	Casting	
ERCCoCr-E	ASME	USA	Casting	
ERCoCr-E	ASME	USA	Casting	
R30021	UNS	USA	Casting	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.