



Material - SAE Inconel 751

Standard Specification for Nickel and Nickel-Related Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - SAE Inconel 751 Nickel and Nickel-Related Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Round Bar

Chemical Composition			Heat Treatment	
Carbon	C %	0.030 - 0.100	As-Cast or Annealing or Age Hardning	
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	14.000 - 17.000		
Aluminium	Al %	1.100 - 1.350		
Copper	Cu %	0.500 max.		
Sulphur	S %	0.015 max.		
Nb + Ta	Nb% + Ta%	0.700 - 1.200		
Phosphorus	P %	0.015 max.	Mechanical Properties	
Iron	Fe %	5.000 - 9.000	Tensile Strength in Mpa	1100 - 1300
Molybdenum	Mo %	0.500 max.	Yield Strength in Mpa	630 - 850
Titanium	Ti %	2.000 - 2.600	Elongation in %	12 - 33
Boron	B %	0.0015 - 0.009	Reduction of Area in %	20 - 32
Cobalt	Co %	1.000 max.	Hardness in HRC	32 - 40
Nickel	Ni %	Balance	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N07751	UNS	USA	Round Bar
NiCr 15 Fe 7 TiAl	ISO	International	Round Bar
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.