GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - SAE J 452 A03600 (360.0)

Standard Specification for Compositions, Mechanical and Physical Properties of SAE Aluminum Casting Alloys

Group - Non-Ferrous Aluminium Alloys

Sub Group - SAE J 452 A03600 (360.0) Compositions, Mechanical and Physical Properties of SAE Aluminum Casting Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Silicon	Si %	9.000 - 10.000
Iron	Fe %	2.000 max.
Copper	Cu %	0.600 max.
Manganese	Mn %	0.350 max.
Magnesium	Mg %	0.400 - 0.600
Nickel	Ni %	0.500 max.
Zinc	Zn %	0.500 max.
Other	Ot %	0.250 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Solution Aging

Mechanical Properties	
Tensile Strength in Mpa	-
Proof Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
A03600	UNS	USA	Casting
360.0000	UNS	USA	Casting
1725 GB-AlSi10Mg	DIN	Germany	Casting
1725 3.2331	DIN	Germany	Casting
1725 GBD-AlSi10Mg	DIN	Germany	Casting
1725 3,2336	DIN	Germany	Casting
1725 GB-AlSi10Mg(Cu)	DIN	Germany	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.