GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - SAE J 462 UNS C86500 Grade B

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloys

Sub Group - SAE J 462 UNS C86500 Grade B Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Tin	Sn %	1.000 max.
Lead	Pb %	0.400 max.
Zinc	Zn %	36.000 - 42.000
Iron	Fe %	0.400 - 2.000
Nickel	Ni %	1.000 max.
Manganese	Mn %	0.100 - 1.500
Aluminium	Al %	0.500 - 1.500
Copper	Cu %	55.000 - 60.000
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	485 min.
Yield Strength in Mpa	170 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in HBW	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
C86500	UNS	USA	Casting
B 271 UNS C86500	ASTM	USA	Casting
B 505 UNS C86500	ASTM	USA	Casting
B 30 UNS C86500	ASTM	USA	Ingots and Casting
B 584 UNS C86500	ASTM	USA	Casting
B 763 UNS C86500	ASTM	USA	Casting
4860 Grade 1	AMS	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.