GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - SAE J 462 UNS C93500 Grade A

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloys

Sub Group - SAE J 462 UNS C93500 Grade A Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Casting

Chemical Composition		
Tin	Sn %	4.300 - 6.000
Lead	Pb %	8.000 - 11.000
Zinc	Zn %	2.000 max.
Iron	Fe %	0.200 max.
Antimony	Sb %	0.300 max.
Nickel	Ni %	1.000 max.
Sulphur	S %	0.080 max.
Phosphorus	P %	0.050 max.
Aluminium	Al %	0.005 max.
Silicon	Si %	0.005 max.
Copper	Cu %	83.000 - 86.000
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	195 min.
Yield Strength in Mpa	85 min.
Elongation in %	15 min.
Reduction of Area in %	-
Hardness in HBW	-
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
C93500	UNS	USA	Casting
B 505 UNS C93500	ASTM	USA	Casting
B 271 UNS C93500	ASTM	USA	Casting
B 763 UNS 93500	ASTM	USA	Casting
B 584 UNS C93500	ASTM	USA	Casting
J 462 UNS C93500 Grade B	SAE	USA	Casting
1982 CuSnPb9	EN	European Union	Ingots and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.