GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - SAE J 463 UNS C34200

Standard Specification for Wrough Copper and Copper Alloys

Group - Non-Ferrous Copper Alloys

Sub Group - SAE J 463 UNS C34200 Wrough Copper and Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Sheet, Strip, Bar, Plate, Rod, Wire, Tube and Shapes

Chemical Composition		
Iron	Fe %	0.100 max.
Lead	Pb %	1.500 - 2.500
Copper	Cu %	62.500 - 66.500
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Raw or Annealing or Hardening

Mechanical Properties	
Tensile Strength in Mpa	545 - 615
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HRB	83 - 89
Impact in Joule	-

www.gravitycastindia.com

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
C34200	UNS	USA	Sheet, Strip, Bar, Plate, Rod, Wire, Tube and Shapes
B 121 UNS C34200	ASTM	USA	Plate, Sheet, Strip and Rolled Bar
2874 CZ131	B.S.	United Kingdom	Rods and Sections
12164 CuZn35Pb2	EN	European Union	Rods
12164 CW601N	EN	European Union	Rods
12166 CuZn35Pb2	EN	European Union	Rods
12166 CW601N	EN	European Union	Rods

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.