



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - SAE J462 65

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloy

Sub Group - SAE J462 Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | | | |
|----------------------|------|-----------------|--|-----------|-----------------------|--|
| Aluminium | Al % | 0.005 max. | As-Cast | | | |
| Iron | Fe % | 0.150 max. | | | | |
| Phosphorus | P % | 0.100 - 0.300 | | | | |
| Lead | Pb % | 0.500 max. | | | | |
| Tin | Sn % | 10.000 - 12.000 | | | | |
| Zinc | Zn % | 0.500 max. | | | | |
| Other | Ot% | 1.000 max. | | | | |
| Copper | Cu % | 88.000 - 90.000 | | | | |
| - | - | - | | | | |
| - | - | - | <th colspan="2">Mechanical Properties</th> | | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 241 - 262 | | |
| - | - | - | Yield Strength in Mpa | 165 min. | | |
| - | - | - | Elongation in % | 8 - 10 | | |
| - | - | - | Reduction of Area in % | - | | |
| - | - | - | Hardness in BHN | - | | |
| - | - | - | Impact in Joule | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|---------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| C90700 | UNS | USA | Rod, Bar, Tube and Shapes |
| B30 C90700 | ASTM | USA | Ingot and Casting |
| B427 C90700 | ASTM | USA | Casting |
| B505 C90700 | ASTM | USA | Casting |
| SB-505 C90700 | ASME | USA | Casting |
| CA907 | SAE | USA | Casting |
| CACIn502 | KS | Korea | Ingot and Casting |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS