



Material - SAE J462 C87400

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloy
Sub Group - SAE J462 Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.800 max.		
Lead	Pb %	1.000 max.	\exists	
Silicon	Si %	2.500 - 4.000	71	
Zinc	Zn %	12.000 - 16.000	As-Cast	
Copper	Cu %	79.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	/		Tensile Strength in Mpa	345 min.
-	-	-	Yield Strength in Mpa	145 min.
-	-	-	Elongation in %	18 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
	-	-	Impac <mark>t in Joule</mark>	

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
C87400	UNS	USA	Rod, Bar, Tube and Shapes	
B271 C87400	ASTM	USA	Casting	
B30 C87400	ASTM	USA	Ingot and Casting	
B584 C87400	ASTM	USA	Casting	
SB-584 C87400	ASME	USA	Casting	
CA874	SAE	USA	Casting	
CACIn803	KS	Korea	Ingot and Casting	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.