



## Material - SAE J462 CA935

### Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloy

Sub Group - SAE J462 Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.200 max.		
Nickel	Ni %	0.800 max.		
Phosphorus	P %	0.050 max.		
Lead	Pb %	8.000 - 11.000		
Antimony	Sb %	0.350 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	4.500 - 6.000		
Zinc	Zn %	2.000 max.		
Other	Ot%	0.200 max.		
Copper	Cu %	83.00 - 86.000	<b>Mechanical Properties</b> Tensile Strength in Mpa      172 - 207 Yield Strength in Mpa      83 - 110 Elongation in %      8 - 12 Reduction of Area in %      - Hardness in BHN      - Impact in Joule      -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C93500	UNS	USA	Rod, Bar, Tube and Shapes
B30 C93500	ASTM	USA	Ingot and Casting
B271 C93500	ASTM	USA	Casting
SB-505 C93500	ASME	USA	Casting
SB-584 C93500	ASME	USA	Casting
C93500	SAE	USA	Casting
C93500	AS	Australia	Ingot and Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.