



Material - SAE J462 CA947

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloy

Sub Group - SAE J462 Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast or Solution Annealing	
Iron	Fe %	0.250 max.		
Manganese	Mn %	0.200 max.		
Nickel	Ni %	4.500 - 6.000		
Other	Ot%	0.250 max.		
Lead	Pb %	0.100 max.		
Antimony	Sb %	0.150 max.		
Silicon	Si %	0.005 max.		
Tin	Sn %	4.500 - 6.000		
Zinc	Zn %	2.500 max.		
Copper	Cu %	85.000 - 90.000	Mechanical Properties Tensile Strength in Mpa 310 - 517 Yield Strength in Mpa 138 - 345 Elongation in % 5 - 25 Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C94700	UNS	USA	Rod, Bar, Tube and Shapes
B292-A	ASTM	USA	Casting
B30 C94700	ASTM	USA	Ingot and Casting
B505 C94700	ASTM	USA	Casting
B584 C94700	ASTM	USA	Casting
SB-505 C94700	ASME	USA	Casting
C94700	SAE	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.