



Material - SAE J462 CA952

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloy

Sub Group - SAE J462 Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	8.500 - 9.500	As-Cast	
Iron	Fe %	2.500 - 4.000		
Other	Ot%	1.000 max.		
Copper	Cu %	86.000 min.		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	448 min.
			Yield Strength in Mpa	172 min.
			Elongation in %	20 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C95200	UNS	USA	Rod, Bar, Tube and Shapes
B148 C95200	ASTM	USA	Casting
B148 Grade A	ASTM	USA	Casting
SB-148 C95200	ASME	USA	Casting
SB-148 Grade A	ASME	USA	Casting
C95200	SAE	USA	Casting
CACIn701	KS	Korea	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.