



Material - SAE J462 CA954

Standard Specification for Cast Copper Alloys

Group - Non-Ferrous Copper Alloy

Sub Group - SAE J462 Cast Copper Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--|--|
| Aluminium | Al % | 10.000 - 11.500 | As-Cast or Solution Annealing or Annealing | |
| Iron | Fe % | 3.000 - 5.000 | | |
| Manganese | Mn % | 0.500 max. | | |
| Nickel | Ni % | 2.500 max. | | |
| Other | Ot% | 0.500 max. | | |
| Copper | Cu % | 83.000 min. | | |
| - | - | - | | |
| - | - | - | Mechanical Properties Tensile Strength in Mpa 517 - 621 Yield Strength in Mpa 207 - 310 Elongation in % 6 - 12 Reduction of Area in % - Hardness in BHN - Impact in Joule - | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|-----------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| C95400 | UNS | USA | Rod, Bar, Tube and Shapes |
| B66 C95400 | ASTM | USA | Casting |
| B148 C95400 | ASTM | USA | Casting |
| SB-148 C95400 | ASME | USA | Casting |
| SB-148 Grade C | ASME | USA | Casting |
| C95400 | SAE | USA | Casting |
| C95400 | AS | Australia | Ingot and Casting |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.