



Material - SAE SIMALLOY 625

Standard Specification for Nickel and Nickel-Related Alloys

Group - Non-Ferrous Nickel Alloys

Sub Group - SAE SIMALLOY 625 Nickel and Nickel-Related Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Pipe and Tube

| Chemical Composition | | | Heat Treatment | |
|----------------------|-----------|-------------|--------------------------------------|------------|
| Carbon | C % | 0.100 max. | | |
| Silicon | Si % | 0.500 max. | As-Cast or Annealing or Age Hardning | |
| Manganese | Mn % | 0.500 max. | | |
| Chromium | Cr % | 21.500 max. | | |
| Molybdenum | Mo % | 9.000 max. | | |
| Aluminium | Al % | 0.400 max. | | |
| Cobalt | Co % | 1.000 max. | | |
| Iron | Fe % | 5.000 max. | | _ |
| Titanium | Ti % | 0.400 max. | Mechanical Properties | |
| Ni + Co | Ni% + Co% | 68.000 min. | Tensile Strength in Mpa | 724 - 1104 |
| - | - | - | Yield Strength in Mpa | 290 - 759 |
| - | - | - | Elongation in % | 30 - 65 |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | 110 - 240 |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| Inconel 625 | SAE | USA | Sheet, Strip and Plate | |
| N06250 | UNS | USA | Sheet, Strip and Plate | |
| B622 N06250 | ASTM | USA | Pipe and Tube | |
| SB-622 N06250 | ASME | USA | Pipe and Tube | |
| F3056 N06625 CLASS A | ASTM | USA | Pipe and Tube | |
| F3056 N06625 CLASS B | ASTM | USA | Pipe and Tube | |
| F3056 N06625 CLASS C | ASTM | USA | Pipe and Tube | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.