



Material - SAE SIMALLOY

Standard Specification for Nickel Alloy, Corrosion and Heat-Resistant, Wire

Group - Non-Ferrous Nickel Alloys

Sub Group - SAE SIMALLOY Nickel Alloy, Corrosion and Heat-Resistant, Wire Application - Intended for Valve, Pump, General Engineering, Automotive and other Industries

Grade Belongs to the Industry - Wire

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Silicon	Si %	0.500 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	15.500 max.	As-Cast or Annealing or Age Hardning	
Aluminium	Al %	0.700 max.		
Copper	Cu %	0.500 max.		
Ca + Ta	Ca% + Ta%	0.900 max.		
Titanium	Ti %	2.500 max.		_
Iron	Fe %	8.000 max.	Mechanical Properties	
Ni + Co	Ni% + Co%	73.000 min.	Tensile Strength in Mpa	759 - 1897
-	-	-	Yield Strength in Mpa	345 - 1656
-	-	-	Elongation in %	2 - 45
-	-	-	Reduction of Area in %	30 - 60
	-		Hardness in HRC	93 min.
-	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
Inconel X750	SAE	USA	Wire	
N07750	UNS	USA	Wire	
UNITEMP 750	SAE	USA	Wire	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.